

Appl. No. 10/007,375  
Amdt. dated August 7, 2003  
Reply to Office Action of May 7, 2003

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (Canceled)
2. (Currently amended): The process of claim 12 wherein said nonwoven fabric of claim 1 having has a basis weight in the range of from about 34 gsm to about 88 gsm.
3. (Currently amended): The process of claim 12 wherein said nonwoven fabric of claim 1 wherein said opposing surfaces have a difference in demonstrated alcohol repellency of at least about 30% when exposed to isopropyl alcohol of varying concentrations.
4. (Canceled)
5. (Currently amended): The nonwoven fabric process of claim [[ 2 ]] 13 wherein said nonwoven fabric opposing surfaces have a difference in demonstrated alcohol repellency of at least about 30% when exposed to isopropyl alcohol of varying concentrations.
6. (Currently amended): The process of claim 12 wherein said nonwoven fabric of claim 1 comprising comprises a spunbond layer and a meltblown layer.
7. (Currently amended): The process of claim 6 wherein said nonwoven fabric of claim 6 comprising comprises a meltblown layer between two spunbond layers.
8. (Currently amended): The process of claim 13 wherein said nonwoven fabric of claim 5 comprising comprises a spunbond layer and a meltblown layer.
9. (Currently amended): The process of claim 12 wherein said nonwoven fabric of claim 6 having has a hydrostatic head of at least about 50mB.
10. (Currently amended): The process of claim 13 wherein said nonwoven fabric of claim 7 having has a hydrostatic head of at least about 50mB.
11. (Currently amended): The process of claim 8 wherein said nonwoven fabric of claim 8 having has a hydrostatic head of at least about 50mB.
12. (Currently amended) A process for treating producing a lightweight nonwoven fabric having opposing first and second surfaces, one of which is rich in antistatic agent and one of which has minimal antistatic agent, said fabric having a treatment add-on in the range of from about 0.017 gsm to about 1.08 gsm and good barrier properties as measured by a rating of at least 3 when measured with 70% isopropyl alcohol for alcohol repellency and less than about 0.50 seconds static decay test.

Received from < 770 587 7327 > at 8/7/03 12:59:09 PM [Eastern Daylight Time]

Appl. No. 10/007,376  
Amdt. dated August 7, 2003  
Reply to Office Action of May 7, 2003

comprising the steps of:

applying an alcohol repellency treatment containing an antistatic agent to a first or both of said surfaces, and in a separate step, applying an antistatic treatment to the second surface only of said fabric.

13. (Previously presented): The process of claim 12 wherein the step of applying an antistatic treatment occurs prior to fully curing the alcohol repellency treatment.